

## Antislip performances

Regulation	Definition	Index	Lux	Satin	Lithos	Vesuvio	Dune	Arena	Fossil	Velluto
DM236/89 BCRA	<b>BCRA Coefficient of Friction</b>	<b>DCOFd average value</b>	0,7	0,59	0,53	0,58	0,57	0,91	0,86	0,59
		<b>DCOFw average value</b>	0,6	0,48	0,61	0,48	0,53	0,88	0,97	0,65
DIN 51130	<b>Anti-slip testing of floor coverings - Shod feet</b>	<b>Group of anti-slip properties</b>	-	-	R10	R10	R10	R13	R13	n.c.
DIN 51097	<b>Anti-slip testing of floor coverings - Bare feet</b>	<b>Classification</b>	-	-	A+B	A+B+C	A+B	A+B+C	A+B+C	A
ANSI A137.1:2012 / A326.3:2017	<b>Tile slip test</b>	<b>DCOFw</b>	0,25	0,46	0,46	0,5	0,42	0,81	0,71	0,43
UNI EN 14231:04	<b>Slip resistance by means of the pendulum tester</b>	<b>DCOFw -USRV</b>	25	22	42	30	37	66	64	38
BS 976/02+A1:2011 United kingdom	<b>Pendulum testers. Method of operation</b>	<b>DCOFd - PTV</b>	38	42	48	55	53	65	-	48
		<b>DCOFw - PTV</b>	16	24	43	50	28	60	-	38
UNE 41901:2017 EX	<b>Unpolished and Polished slip/skip resistance</b>	<b>DCOFw</b>	25	30	55	42	31	68	-	38

Disclaimer: the values shown above are average values that may slightly change among different batches.